

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
23 October 2003 (23.10.2003)

PCT

(10) International Publication Number
WO 03/087016 A1

- (51) International Patent Classification⁷: C04B 35/58, C22C 29/18, H05B 3/14
- (21) International Application Number: PCT/SE03/00556
- (22) International Filing Date: 4 April 2003 (04.04.2003)
- (25) Filing Language: Swedish
- (26) Publication Language: English
- (30) Priority Data:
0201042-9 5 April 2002 (05.04.2002) SE
0201043-7 5 April 2002 (05.04.2002) SE
- (71) Applicant (for all designated States except US): SANDVIK AB [SE/SE]; S-811 81 Sandviken (SE).
- (72) Inventors; and
- (75) Inventors/Applicants (for US only): SUNDBERG, Mats [SE/SE]; Liljanstorpssvägen 57, S-722 46 Västerås (SE). MAGNUSSON, Anders [SE/SE]; Skultunavägen 62, S-722 17 Västerås (SE).
- (74) Agents: ÖRTENBLAD, Bertil et al.; Noréns Patentbyrå AB, Box 10198, S-100 55 Stockholm (SE).
- (81) Designated States (national): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NI, NO, NZ, OM, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.
- (84) Designated States (regional): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO, SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).
- Published:
— with international search report
- For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: METHOD OF MAKING A HEATING ELEMENT OF MOLYBDENUM SILICIDE TYPE

(57) Abstract: The present invention relates to a method of producing a heating element that is comprised essentially of molybdenum silicide and alloys of this basic material, which forms aluminium oxide on its surface. The invention is characterised by producing a material that contains substantially $\text{Mo}(\text{Si}_{1-x}\text{Al}_x)_2$ and Al_2O_3 by mixing a mixture of a silicon and molybdenum compound with an aluminium compound; in that the silicon and molybdenum compound either include $\text{Mo}(\text{Si}_{1-y}\text{Al}_y)_2$ and are mixed either with an aluminium compound consisting of Al_2O_3 or $\text{Al}(\text{OH})_3$ and possibly mixed with one or more of the compounds SiO_2 , Si and MoO_3 or by virtue of the mixture of the silicon and molybdenum compound containing MoO_3 and Al and Si and/or SiO_2 ; in that the input components together have a degree of purity corresponding to at least 98%; and in that the mixture is caused to react exothermically and/or by being sintered so that exchange reactions are caused to take place, to form the compounds $\text{Mo}(\text{Si}_{1-x}\text{Al}_x)_2$ and Al_2O_3 , where x is caused to lie in the range of 0.4 - 0.6.

Method of making a heating element of molybdenum silicide type.

The present invention relates to a method of manufacturing a
5 heating element of the molybdenum silicide type.

An electric resistance element of the molybdenum silicide type is described in Swedish Patent Specifications 0003512-1 and 0004329-9. According to patent specification 0003512-1
10 the resistance material of the heating element includes $\text{Mo}(\text{Si}_{1-x}\text{Al}_x)_2$ which is caused to contain aluminium to an extent at which the formation of pest is essentially prevented.

It has been found that when such material is operated in a
15 temperature range of 400 - 600°C no pest, or only a slight amount of pest, is formed. Pest is formed by virtue of the formation of MoO_3 from MoSi_2 and O_2 .

The reason why the formation of pest is significantly reduced
20 or is eliminated is due the formation of Al_2O_3 , or a layer rich in Al_2O_3 , on the surface of the element

The other patent specification 0004329-9 teaches a method of increasing the useful life span of heating elements that
25 essentially consist of molybdenum silicide and alloys of this basic material when the element operates at high temperatures.

According to this patent specification, the heating element
30 is caused to contain aluminium to an extent which is sufficient to maintain a stable, slowly growing layer of aluminium oxide on the surface of the heating element.

According to one preferred embodiment the heating element material is caused to contain $\text{Mo}(\text{Si}_{1-x}\text{Al}_x)_2$, where x lies in the range of 0.2 - 0.6.

5 A material of the molybdenum silicide type that contains aluminium has been found to possess improved corrosion properties at both low and high temperatures.

Such material is often produced by mixing MoSi_2 powder with
10 oxidic raw material, such as aluminosilicates. When the raw material is bentonite clay, there is obtained a relatively low melting point which contributes towards so-called smelt phase sintering which results in dense materials that contains MoSi_2 and a proportion of aluminium silicate corresponding to 15 - 20 percent by volume.
15

Bentonite clay containing chiefly SiO_2 can be used in the production of heating elements containing $\text{Mo}(\text{Si}_{1-x}\text{Al}_x)_2$. When sintering with an Al-alloyed silicide there takes place a
20 chemical exchange reaction in which the greater affinity of the oxygen to Al than to Si results in Si leaving the aluminium silicate and entering the silicide as a result of Al leaving the silicide and being sucked up by the oxide phase. This exchange reaction also contributes towards improved
25 sintering properties of the composite material. The final material contains $\text{Mo}(\text{Si}_{1-x}\text{Al}_x)_2$ that is substantially depleted of Al, where the oxide phase contains Al_2O_3 in all essentials.

The standard procedure of manufacture involves mixing molybdenum, silicon and aluminium in powder form and firing the
30 powder mix normally under a shielding gas atmosphere. This results in a cake of the material $\text{Mo}(\text{Si}_{1-y}\text{Al}_y)_2$, where y is larger than x in the above formula as a result of said ex-

change reaction. The reaction is exothermic. The cake is then crushed and ground down to a fine particle size normally in the order of 1 - 20µm. This powder is mixed with bentonite clay such as to form a wet ceramic material. The material is extruded and dried to a rod form whose diameter corresponds to the diameter of the subsequent heating element. The material is then sintered at a temperature that exceeds the smelting temperature of the bentonite component.

However, there is a drawback with an element of this kind. The problem is that the oxide that forms on the surface of the element, namely Al_2O_3 , sometimes, peels away or flakes off, i.e. loosens from the surface of the element in cyclic operation.

A peeling oxide gives poorer protection against continued oxidation of aluminium which becomes impoverished in the outer surface of the element more quickly. Moreover, oxide peelings can contaminate the oven in which the element is fitted, with the risk that performance and the appearance of products heat treated in ovens that have such elements will be significantly impaired. This thus restricts the use of such elements in heating processes.

This problem is solved by the solution taught in each of the two Swedish Patent Specifications 0201042-9 and 0201043-7.

Swedish Patent Specification 0201042-9 teaches a method of producing a heating element that comprises substantially of molybdenum silicide and alloys of this basic material. The method is characterised by producing a material that contains chiefly $\text{Mo}(\text{Si}_{1-x}\text{Al}_x)_2$ and Al_2O_3 by mixing molybdenum alumi-

nosilicide $(\text{Mo}(\text{Si}_{1-y}\text{Al}_y)_2)$ with SiO_2 , where the SiO_2 is at least 98% pure.

Swedish Patent Specification 0201043-7 teaches the production of a corresponding material, where bentonite clay is used to add silicon dioxide and aluminium oxide. The bentonite clay shall have a contaminating substance content of less than 2000ppm.

It has been found surprisingly that there is obtained at low contaminant consistencies an oxide which does not peel after cyclic operation between room temperature and high temperatures, for instance 1500°C . The present invention is based on the insight that such a pure aluminium-oxide building molybdenum silicide material can be produced beneficially by beginning partly with other material and compounds than those given above.

The present method of production of a heating element that is comprised essentially of molybdenum silicide and its alloys includes the step of producing a material that contains essentially $\text{Mo}(\text{Si}_{1-x}\text{Al}_x)_2$ and Al_2O_3 by mixing a mixture of silicon and molybdenum compound with an aluminium compound.

According to the invention silicon and the molybdenum compound include $\text{Mo}(\text{Si}_{1-y}\text{Al}_y)_2$ and are mixed with either an aluminium compound consisting of Al_2O_3 or $\text{Al}(\text{OH})_3$, and are optionally mixed with one or more of the compounds SiO_2 , Si and MoO_3 .

According to a second embodiment, silicon and the molybdenum compound contain MoO_3 and Al and Si and/or SiO_2 .

According to the invention the input components together have a degree of purity of at least 98%.

According to a preferred embodiment of the invention the
5 input components have a degree of purity of at least 99%.

The mixture is caused to react exothermically and/or by being sintered so that exchange reactions take place, to form the compounds $\text{Mo}(\text{Si}_{1-x}\text{Al}_x)_2$ and Al_2O_3 , where x is caused to lie in
10 the range of 0.4 - 0.6.

There is obtained by this method an element material that is aluminium oxide building and whose aluminium oxide layers will not peel or flake; which was mentioned as a problem in
15 the beginning of this document.

According to one preferred embodiment x is caused to lie in the range of 0.45 - 0.55.

20 According to one preferred embodiment the SiO_2 is included in silicates, where remaining substances in the silicate have properties that molybdenum silicide is unable to alloy with said substance or substances and have such properties that the symmetry of the crystal lattice of the molybdenum silicide is retained.
25

It is possible to substitute molybdenum partly with Re, W or Nb in the material $\text{Mo}(\text{Si}_{1-x}\text{Al}_x)_2$ without changing the symmetry of the crystal lattice.

30 Molybdenum can be replaced with tungsten (W) by an amount corresponding approximately to one third.

According to one preferred embodiment one or more of the following sintering auxiliaries MgO, CaO, SiO₂ and Y₂O₃ is/are caused to be added to the mixture.

- 5 The present invention thus solves the problem mentioned in the introduction and enables the present element to be used beneficially in ovens without detriment to the material treated in the oven.
- 10 The present invention shall not be considered to be limited to the aforescribed embodiments, since variations can be made within the scope of the accompanying claims.

CLAIMS

1. A method of producing a heating element that is comprised essentially of molybdenum silicide and alloys of this basic material, which forms aluminium oxide on its surface, characterized by producing a material that contains substantially $\text{Mo}(\text{Si}_{1-x}\text{Al}_x)_2$ and Al_2O_3 by mixing a mixture of a silicon and molybdenum compound with an aluminium compound; in that the silicon and molybdenum compound either include $\text{Mo}(\text{Si}_{1-y}\text{Al}_y)_2$ and are mixed with either an aluminium compound consisting of Al_2O_3 or $\text{Al}(\text{OH})_3$ and possibly mixed with one or more of the compounds SiO_2 , Si and MoO_3 or by virtue of the mixture of the silicon and molybdenum compound containing MoO_3 and Al and Si and/or SiO_2 ; in that the input components together have a degree of purity corresponding to at least 98%; and in that the mixture is caused to react exothermically and/or by being sintered so that exchange reactions are caused to take place, to form the compounds $\text{Mo}(\text{Si}_{1-x}\text{Al}_x)_2$ and Al_2O_3 , where x is caused to lie in the range of 0.4 - 0.6.
2. A method according to Claim 1, characterized in that said SiO_2 is included in silicates, where remaining substances in the silicate have properties such that molybdenum silicide is unable to alloy with said substance or substances and have such properties that the symmetry of the crystal lattice of the molybdenum silicide is retained.
3. A method according to Claim 1 or 2, characterized in that x is caused to lie in the range of 0.45 - 0.55.
4. A method according to Claim 1 2 or 3, characterized by adding one or more of the following sintering auxiliaries MgO , CaO , SiO_2 and Y_2O_3 to said mixture.

5. A method according to Claim 1 2, 3 or 4, c h a r a c t -
e r i s e d by substituting molybdenum partly with Re or W
or Nb in the material $\text{Mo}(\text{Si}_{1-x}\text{Al}_x)_2$.

5

6. A method according to Claim 5, c h a r a c t e r i s e d
by replacing molybdenum with W in an amount corresponding to
approximately one third.

10 7. A method according to any one of the preceding Claims,
c h a r a c t e r i s e d in that the input components have a
degree of purity of at least 99%.

INTERNATIONAL SEARCH REPORT

International application No.

PCT/SE 03/00556

A. CLASSIFICATION OF SUBJECT MATTER

IPC7: C04B 35/58, C22C 29/18, H05B 3/14

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC7: C04B, C22C, H05B

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

SE,DK,FI,NO classes as above

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

WPI DATA, EPO-INTERNAL

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	DE 179100 A (METALLWERK PLANSEE GESELLSCHAFT M.B.H. IN REUTTE (TIROL)), 10 July 1954 (10.07.54) --	1-7
A	US 3269806 A (ERICH FITZER ET AL), 30 August 1966 (30.08.66) --	1-7
A	GB 899464 A (AKTIEBOLAGET KANTHAL), 20 June 1962 (20.06.62) -- -----	1-7

☐ Further documents are listed in the continuation of Box C.☒ See patent family annex.

* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"B" earlier application or patent but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance: the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance: the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

"&" document member of the same patent family

Date of the actual completion of the international search

18 June 2003

Date of mailing of the international search report

30-06-2003

Name and mailing address of the ISA/

Swedish Patent Office

Box 5055, S-102 42 STOCKHOLM

Facsimile No. +46 8 666 02 86

Authorized officer

Ulrika Nilsson/MP

Telephone No. +46 8 782 25 00

INTERNATIONAL SEARCH REPORT

International application No.

PCT/SE 03/00556

Patent document cited in search report			Publication date	Patent family member(s)	Publication date
DE	179100	A	10/07/54	NONE	
US	3269806	A	30/08/66	CH 479221 A	30/09/69
				DE 1243078 B	22/06/67
				GB 993499 A	26/05/65
				SE 305404 B	21/10/68
GB	899464	A	20/06/62	DE 1161038 B	09/01/64

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ **BLACK BORDERS**
- ☐ **IMAGE CUT OFF AT TOP, BOTTOM OR SIDES**
- ☒ **FADED TEXT OR DRAWING**
- ☒ **BLURRED OR ILLEGIBLE TEXT OR DRAWING**
- ☐ **SKEWED/SLANTED IMAGES**
- ☐ **COLOR OR BLACK AND WHITE PHOTOGRAPHS**
- ☐ **GRAY SCALE DOCUMENTS**
- ☐ **LINES OR MARKS ON ORIGINAL DOCUMENT**
- ☐ **REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY**
- ☐ **OTHER:** _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.